

**WHAT IS CLAIMED IS:**

- 1 1. A photographic element comprising:
  - 2 a transparent film support;
  - 3 a blue recording layer coated on the support, the blue recording layer
  - 4 comprising a first image dye-forming coupler and radiation-sensitive silver halide
  - 5 grains for forming a developable latent image upon imagewise exposure;
  - 6 a green recording layer coated on the support, the green recording layer
  - 7 comprising a second image dye-forming coupler and radiation-sensitive silver halide
  - 8 grains for forming a developable latent image upon imagewise exposure;
  - 9 a red recording layer coated on the support, the red recording layer comprising
  - 10 a third image dye-forming coupler and radiation-sensitive silver halide grains for
  - 11 forming a developable latent image upon imagewise exposure; and
  - 12 wherein the radiation-sensitive silver halide grains in each recording layer
  - 13 comprises at least a first and second set of radiation-sensitive silver halide grains, the
  - 14 first set of radiation-sensitive silver halide grains having a higher maximum
  - 15 sensitivity and a faster development time than the second set of radiation-sensitive
  - 16 silver halide grains.
- 1 2. The photographic element as recited in claim 1 wherein the first image dye-
- 2 forming coupler forms a yellow image dye, the second image dye-forming coupler
- 3 forms a magenta image dye, and the third image dye-forming coupler forms a cyan
- 4 image dye.

PATENT APPLICATION

1 3. The photographic element as recited in claim 1 wherein the first and second  
2 sets of radiation-sensitive silver halide grains are disposed within a single emulsion  
3 layer.

1 4. The photographic element as recited in claim 1 wherein the first set of  
2 radiation-sensitive silver halide grains are disposed within a first emulsion layer and  
3 the second set of radiation-sensitive silver halide grains are disposed within a second  
4 emulsion layer.

1 5. The photographic element as recited in claim 1 wherein the radiation-sensitive  
2 silver halide grains further comprises a third set of radiation-sensitive silver halide  
3 grains having a maximum sensitivity and a development time between that of the first  
4 set of radiation-sensitive silver halide grains and the second set of radiation-sensitive  
5 silver halide grains.

1 6. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by increasing  
3 the amount of less-soluble halide within the composition of the second set of  
4 radiation-sensitive silver halide grains.

1 7. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using a  
3 development retarder as an emulsion addenda.

PATENT APPLICATION

1 8. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using an  
3 antifoggant.

1 9. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using an  
3 antifoggant with solubilizing groups which diffuse away and diminish in activity over  
4 time.

1 10. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using a  
3 development retarding spectral-sensitizing dye.

1 11. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using a  
3 development retarding spectral-sensitizing dye with added solubility function groups  
4 which diffuse away with time.

1 12. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using an  
3 emulsion stabilizer.

1 13. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by using an  
3 emulsion stabilizer with solubilizing groups.

1 14. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by reducing the  
3 level of chemical sensitization.

1 15. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by altering the  
3 type of chemical sensitization.

1 16. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by removal of  
3 reduction sensitization.

1 17. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by  
3 encapsulating the second set of radiation-sensitive silver halide grains.

1 18. The photographic element as recited in claim 1 wherein the development time  
2 of the second set of radiation-sensitive silver halide grains is retarded by including  
3 developer inhibiting/releasing agents within the emulsion.

PATENT APPLICATION

- 1 19. The photographic element as recited in claim 1 wherein the development time  
2 of the first set of radiation-sensitive silver halide grains is accelerated by using  
3 accelerators.

2005-10-10 10:10:10